

# OVERCOAT 2020 GLOSS WHITE

<b>DESCRIPTION</b>	A high quality, fast dry, rust inhibitive aerosol enamel.
<b>USES</b>	Use on most metal surfaces, or as touch up on Topcoat-1010 USDA White.
<b>APPEARANCE</b>	Gloss White
<b>RECOMMENDED PRIMERS</b>	Primelife 5150 or any bulk Burke Industrial Coatings primer.
<b>PROPELLANT</b>	Propane Isobutane
<b>PHYSICAL PROPERTIES</b>	
CAN PRESSURE:	60 PSI @ 70°F.
ADHESION	Rate excellent
FLEXIBILITY	Full bend over 1/8" mandrel
TEMPERATURE RESISTANCE	300°F
DRY TIMES @ 70°F - 80°F (21° - 27°C) AND 50% RH	
Dry to touch	10 minutes
Recoat	30 minutes
Hard cure	2 hours

## SAFETY INFORMATION

VOC (%)	79%
FLASH POINT	Aerosol - 4°F (T.O.C.)

For specific safety information refer to the **Material Safety Data Sheet**.

FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN

## PRODUCT ORDERING INFORMATION: OVERCOAT 2020 GLOSS WHITE

Product number	Size	Wt./Case	Case Quantity
14-1413-00	16 oz. can	7 lb.	6 or 12 (Sold only by case)

BURKE INDUSTRIAL COATINGS  
600 S. 74<sup>th</sup> Place, Suite 108, Ridgefield, WA 98642  
Tel: (360) 887-8819 Fax: (360) 887-8825  
Customer Service (800)348-3245

