

OVERCOAT 2020 MARINE BLUE

| | |
|----------------------------|-----------------------------------------------------------------------------------|
| DESCRIPTION | A high quality, fast dry, metallic blue aerosol enamel. |
| USES | Use on most metal surfaces, or use as touch up on Superlife Marine Blue products. |
| APPEARANCE | Low sheen metallic enamel |
| RECOMMENDED PRIMERS | Primelife 5150 or any bulk Burke Industrial Coatings primer. |
| PROPELLANT | Propane Isobutane |

PHYSICAL PROPERTIES

| | |
|----------------------------------------------------|-----------------------------|
| CAN PRESSURE: | 60 PSI @ 70°F. |
| ADHESION | Rate excellent |
| FLEXIBILITY | Full bend over 1/8" mandrel |
| TEMPERATURE RESISTANCE | 300°F |
| DRY TIMES @ 70°F - 80°F (21° - 27°C) AND 50% RH | |
| Dry to touch | 10 minutes |
| Recoat | 30 minutes |
| Hard cure | 2 hours |

SAFETY INFORMATION

| | |
|-------------|-------------------------|
| VOC (%) | 79% |
| FLASH POINT | Aerosol - 10°F (T.O.C.) |

For specific safety information refer to the **Material Safety Data Sheet**.

FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN

PRODUCT ORDERING INFORMATION: OVERCOAT 2020 MARINE BLUE

| Product number Quantity | Size | Wt./Case | Case |
|----------------------------|------------|----------|-----------------------|
| 14-2020-00 | 16 oz. can | 7 lb. | 6 (Sold only by case) |

BURKE INDUSTRIAL COATINGS
600 S. 74th Place, Suite 108, Ridgefield, WA 98642
Tel: (360) 887-8819 Fax: (360) 887-8825
Customer Service (800)348-3245